



1150 EBM TEXTURE COAT By Imco®

DESCRIPTION

1150 EBM TEXTURE COAT is a weather resistant, breathable coating that decorates as it protects. It is a flexible membrane type coating that will bridge and seal minor cracks and hide minor surface defects.

BASIC USES

1150 EBM TEXTURE COAT is used on interior or exterior surfaces wherever a decorative lightly texture protective coating is required. **1150 EBM TEXTURE COAT** can be used to coat virtually all normal construction materials, concrete, drywall, cement board, masonry, wood, previously painted surfaces etc.

MAJOR ADVANTAGES OF 1150 EBM TEXTURE COAT

- Non-Toxic
- Non-Flammable
- Interior or exterior applications, unaffected by sun or acid rain
- Flexible - Will not crack or peel
- Freeze Thaw resistant
- Fills porous surfaces, bridges minor hairline cracks
- Hides minor surfaces defects
- Weatherproof - prevents water penetration yet allows substrate to breath
- Water clean-up

TECHNICAL AND PRODUCT DATA

• Flash Point	none	No. of Components	One
• Cure Time:		Reducer/Cleaner	Water
-touch	1 hour	Shelf Life	1 year unopened
-full cure	12 hours	Weight/Litre	1.85 kg(15.4 lbs/gal)
• Pot life:	Indefinite	Coverage	2m2 (21.5 sq.ft)/L
• Min. Application temp.:	5°C/41°F	Packaging	4L/20L pails
• Permeability :	5 perms		(1 gal./5 gal.)
• Flexibility at: -26°C/-15°F	passes 1/8	Colours	Black, Grey, White
• U.V. resistance:	Excellent	Other colours-special order	
• Thermal-shock resistance:	Excellent		

DO NOT ALLOW TO FREEZE

1150

EBM TEXTURE COAT

By Imco®

APPLICATION INSTRUCTIONS

All surfaces must be sound, clean and free of oil, grease, efflorescence, from release agents, wax or other contaminants. Refer to manufacture's Application Procedures and Specifications for more detailed instructions. Brush, roller or spray apply one coat of 1130 EBM WATERPROOFING MEMBRANE to prepared substrate at a minimum rate of 8m² (86SF)/4L, allow 4 to 8 hours to cure and then apply **1150 EBM TEXTURE COAT** by brush, roller or texture gun directly onto the prepared surface .

New concrete - Must be fully cured and free of laitance, form release agents, surface hardeners or any other foreign materials.

Old concrete - All damaged or oil impregnated concrete should be replaced. If laitance or efflorescence is present then etch surface with a 10% Muriatic acid solution, rinse, neutralize, dry and the prime with IMCO® 1115 EBM BASE.

Coated surfaces - All loose, flaking and partially adhered coatings must be removed.

Masonry - Must be free of excess moisture. Masonry walls must be provided with a damp course and weep holes in accordance with good trade practice.

Drywall & cement board - Must be sound and securely fastened with flat head non-rusting screws.

Cracks - **1150 EBM TEXTURE COAT** will bridge minor non-moving cracks. Larger cracks and spalls must be filled before application of coatings

SPECIAL HANDLING

Do not apply the **EBM** coatings in temperatures below 4°C(40°F) or if the temperature will drop below 0°C(32°F) in the next 12 hours or if rain is imminent or if dew will settle before coatings dry

SAFETY

Please refer to MSDS at www.imcotechnologies.com. The **1150 EBM TEXTURE COATINGS** are water-based non-flammable and emit no toxic odours, however, normal precautions should be observed when applying these coatings. In case of eye-splash, flush with large quantities of water and see a physician. If swallowed, see a physician immediately. Keep out of reach of children.

WARRANTY DISCLAIMER

The information herein is to assist customers in determining whether our products are suitable for their application. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to the contents and suitability. We warrant that our products will meet our written specifications. Nothing herein shall constitute a warranty expressed or implied, including any warranty of merchantability or fitness, nor is protection from any loss or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.